



LOBOPUR FONDO AD879 BLANCO

DESCRIPTION

Product whose most important characteristics are its good adhesion on SMC and ABS (*), good hardness and flexibility, as well as very good resistance to the elements.

(*) For other types of plastics consult.

FIELD OF APPLICATION: Paint of SMC and ABS.

TECHNICAL CHARACTERISTICS

| | <u>"A"</u> | <u>"B"</u> | <u>"A" + "B"</u> |
|-------------------------------|--|--------------------------------|---|
| <i>Presentation:</i> | | | Two components |
| <i>Color:</i> | | | White |
| <i>Finish:</i> | | | 85 ± 5% Gardner 60 ^º |
| <i>Specific weight:</i> | 1,22 ± 0,05 gr./cm³ | 1,07 gr./cm³ | 1,19 ± 0,05 gr./cm³ |
| <i>Supply viscosity</i> | 100 ± 10" CF n ^º 4 at 20 ^º C | | |
| <i>% Weight of solids:</i> | 60,3 ± 2% | 75% | 62,6 ± 2% |
| <i>% Volume of solids:</i> | 45,1 ± 2% | 70 ± 2% | 49,6 ± 2% |
| <i>Catalyst:</i> | | CAT 1800 | |
| <i>Proportion of mix.:</i> | | | 19% weight |
| <i>Recommended Thickness:</i> | | | 35 -45 microns |
| <i>Dry:</i> | | | 5-10' pre-dry + 25' at 80 ^º C. |
| <i>Application:</i> | | | Aerographic gun |
| <i>Indicated thinner:</i> | | | DIL. 1033 |
| <i>VOC supply:</i> | 484 gr./lt. | 268 gr./lt. | 446 gr./lt. |

METHOD OF APPLICATION

Apply plastic parts to exhaustive degreasing.

Brush: Not appropriate.

Roller: Not suitable.

Aerographic spry gun: Dilute with approx. 20% DILUENT 1033.

Catalyzing: 19% with CAT 1800 (100 pp Paint / 19 pp cat)

Pot life: minimum 8 hours

Drying: 5-10 'predried + 25' at 80 ° C

Airless spray gun: Not suitable.

Immersion: Not suitable.

Euroquímica Paints, S.A.

Ctra. Argentona – Dosrius, Km 2 – 08319 DOSRIUS (Barcelona) ESPAÑA

Telf.: +34 937 974 300 - Fax: +34 937 919 261

<http://www.euroquimica.com> - E-mail: euroquimica@euroquimica.com

Acreditación Sistema de Calidad





Euroquímica

Protective Coatings & Industrial Paints

CHARACTERISTICS OF THE DRY FILM

Excellent adhesion, hardness and flexibility.

PRECAUTIONS

It is advisable to perform the application in a well-ventilated area or with a plentiful forced-air supply.
Personal safety measures should be taken in order to avoid ingestion, inhalation or contact with the skin.
The normal precautions for fire prevention should be taken during applications.
Keep containers well sealed after use. Do not pour waste down the drain.
Storage stability: 1 year in their original, sealed containers, in good storage conditions.

OBSERVATIONS

We guarantee the quality of our products pursuant to our general terms of sale and supply. Our technical tips for use, expressed verbally, in writing or in tests, are offered in accordance with our current know-how and experience. They are mere indications, which do not imply our responsibility, nor do they exempt you from the need to check for yourselves that the products we supply do meet the procedures and goals you seek, by conducting your own controlling and testing. Application and use of the products is beyond our control and, consequently, depends exclusively on your own personal responsibility, and we decline responsibility for results other than those set out here. Our recommendations regarding safety should not prevent you from determining your own measures, adapted to the conditions of your installations. We reserve the right to modify the contents hereof, without prior notice, in accordance with their technological development.

LOBOPUR AD879 BLANCO - Edition 24-10-11 - Voids all previous issues.

Euroquímica Paints, S.A.

Ctra. Argentona – Dosrius, Km 2 – 08319 DOSRIUS (Barcelona) ESPAÑA
Telf.: +34 937 974 300 - Fax: +34 937 919 261
<http://www.euroquimica.com> - E-mail: euroquimica@euroquimica.com

Acreditación Sistema de Calidad

